

# Technical Information

## 40-40 HS Clear



### 2K Universal Clear

HS clearcoat for high quality

Clear for baslac basecoat 35-

- High solids content, excellent weathering resistance
- Good polishing behaviour
- High gloss, high finish quality

## Application

	<b>Mixing Ratio</b> 2:1+10 %	100 % by volume	40-40
		50 % by volume	50-20, -30
		10 % by volume	60-10, -20, -30, -40
	<b>Spray viscosity at 20°C</b>	DIN 4: 18-20 s	
	<b>Potlife at 20°C</b>	4 h	
	<b>HVLP spray gun</b>		
	Nozzle size	1.3 mm	
	Application pressure	2 bar	
	Nozzle pressure	0.7 bar	
	<b>Compliant gravity-feed spray gun</b>		
	Nozzle Size	1.3-1.4 mm	
	<b>Number of spraycoats</b>	2	
	<b>Film thickness</b>	50-70 µm	
	<b>Flash-off at 20°C</b>	2-3 min after each spray coat	

### Safety advice:

The products are suitable for professional use only.  
It cannot be ruled out that this product contains particles < 0.1 µm.

The data contained in this publication are based on our current knowledge and experience. In view of the many factors that may affect processing and application of our products, these data do not relieve processors from carrying out their own investigations and tests; neither do these data imply any guarantee of certain properties, nor the suitability of the products for a specific purpose. Any descriptions, drawings, photographs, data, proportions, weights etc. given herein are for general information purpose only; they may change without prior information and do not constitute the agreed contractual quality of the products (product specification). It is the responsibility of the recipient of our products to ensure that any proprietary rights and existing laws and legislation are observed.

# Technical Information


## 40-40 HS Clear

2K Universal Clear



### Drying

	Drying at 20 °C	8 h
	Drying at 60 °C	30 min
	Infrared (short wave)	8 min
	Infrared (medium wave)	10-15 min



#### Safety advice:

The products are suitable for professional use only.  
It cannot be ruled out that this product contains particles < 0.1 µm.

The data contained in this publication are based on our current knowledge and experience. In view of the many factors that may affect processing and application of our products, these data do not relieve processors from carrying out their own investigations and tests; neither do these data imply any guarantee of certain properties, nor the suitability of the products for a specific purpose. Any descriptions, drawings, photographs, data, proportions, weights etc. given herein are for general information purpose only; they may change without prior information and do not constitute the agreed contractual quality of the products (product specification). It is the responsibility of the recipient of our products to ensure that any proprietary rights and existing laws and legislation are observed.